



## POLI-PRINT 930 White Gloss R

### Technical Data

Carrier:	Monomeric PVC film, highly stabilized, calendered	
Thickness:	100 $\mu$	(ISO 4593)
Adhesive:	Clear Acrylic Dispersion, removable	
Adhesion:	2,5 N/cm	(Finat FTM 1, after 24 hrs. on Stainless steel)
Dimensional stability:	Shrinkage < 0,4 mm	(Finat FTM 14)
Liner:	One-sided clay-coated Silicone paper (135 g/m <sup>2</sup> )	
Tensile strength md:	> 20 MPa	(DIN EN ISO 527)
Tensile strength cd:	> 20 MPa	(DIN EN ISO 527)
Elongation md:	> 160 %	(DIN EN ISO 527)
Elongation cd:	> 180 %	(DIN EN ISO 527)
Application temperature:	> + 10 °C	
Temperature durability:	- 40 °C - +80 °C	
Outdoor durability:	4 years (unprinted material, vertical outdoor exposure, central European normal climate)	

### Safety Data Sheet

When used under normal conditions, this product does not generate or release any dangerous substances or hazardous chemicals. This is a non-hazardous product in accordance with the current GefStoffV and EU criteria.

This product is not a hazardous product with regards to transportation legislation; neither does it contain substances that are hazardous to water within the meaning of the federal water act. After use, dispose of the waste product in accordance with the local / national authorities.



Version: 17/07/2013

The following technical details are issued to the best of our knowledge, however, without any responsibility for results due to several different kinds of material and application processes. Therefore, we highly recommend that before every usage a test should be conducted on the original material.



## POLI-PRINT 930 White Gloss R

### General Product Information

- POLI-PRINT 930 White Gloss R is a Monomeric PVC-Film (white gloss, 100 µ)
- Laminated with a one-sided clay-coated silicone paper (135 g/m<sup>2</sup>) and equipped with a clear dispersion acrylic adhesive (removable)
- Suitable for bonding various surfaces for example on commercial slabs, glass, metal or plastic
- Especially suitable for the use on smooth as well as slightly curved surfaces
- POLI-PRINT 930 White Gloss R is ideal for short term presentation of advertising panels

### Product Advantages

- Very good opacity and flatness characteristics
- Excellent dimensional stability
- If applied properly, no adhesive residues will be left
- Fire classification B1 Certification and in accordance to DIN 4102-1 flame resistant adhered on steel surface
- The film is resistant to the influence of solvent inks during the printing process and excellent printing results are guaranteed with all customary market ECO-Solvent, Solvent, UV and Latex printers

### Processing Details and Printing Information

- The print must be completely dry before laminating, a minimum of 48 hours drying time is recommended
- The surface which is to be laminated should be free from any impurities to achieve optimal adhesion to the digital printed film

### Transport & Storage

- 2 years if stored in original packaging at ca. 22° C and 50-55% relative humidity
- Printed material should be completely dry and protected during transportation
- Temperature and humidity fluctuations should be avoided



Version: 17/07/2013

The following technical details are issued to the best of our knowledge, however, without any responsibility for results due to several different kinds of material and application processes. Therefore, we highly recommend that before every usage a test should be conducted on the original material.



Adelaide  
08 8277 7733

Brisbane  
07 3808 7277

Gold Coast  
07 5593 8288

Melbourne  
03 8480 0800

Perth  
08 9244 4433

Sydney  
02 9832 7000